

NGO employs a complex blended oil lubrication system, uniformly distributed throughout the product, guaranteeing constant performance over the whole service life of this exceptional oil-loaded nylon. Excellent sliding frictional properties, abrasion resistance and anti stick/slip performance make NGO a first choice for unlubricated moving parts

PROPERTY	TEST METHOD	NOTES	METRIC UNITS		IMPERIAL UNITS	
GENERAL						
Colour			Green Yellow			
Density	ISO1183:1997	Test Method A	g/cm³	1.138	lb/inch³	0.041
Moisture Absorption (Equilibrium)	ISO 62:1999	50% RH, 23C	%	2	%	2
Water Absorption (24 Hours)	ISO 62:1999 (modified)	Immersion, 23C	%	0.2	%	0.2
Water Absorption (Saturation)	ISO 62:1999	Immersion, 23C	%	6.1	%	6.1
FDA Compatibility		YES				
MECHANICAL						
Tensile strength	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	74-78	psi	10732 - 11312
E-modulus	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	3500-3700	psi	507632 - 536639
Elongation at break	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	%	<30	%	<30
Compressive Strength	ISO 604:2002	Sample Type B, 5mm min ⁻¹	MPa	110-120	psi	15954 - 17404
Compressive Modulus	ISO 604:2002	Sample Type A, 1mm min ⁻¹	MPa	2100-2500	psi	304579 - 362594
Flexural Strength*	ISO 178:2001	1.5mm min ⁻¹	MPa	105-125	psi	15229 - 18129
Flexural Modulus	ISO 178:2001	1.5mm min ⁻¹	MPa	3300-3600	psi	478624 - 522135
Izod Impact Strength	ISO 180:2000	Sample Type A (Notched)	KJ/m²	5 - 6.5	ft.lb/in²	2.38 - 3.093
Charpy Impact Strength	ISO 179-2:1999	Notched	KJ/m²	-	ft.lb/in²	-
Hardness (Shore D)	ISO 868:2003	-	-	82	-	82
Coefficient of Friction (Dynamic)	-	31.4m/min, 1.75MPa	-	0.089	-	0.19
Limiting PV	-	-	MPa/m.min	100	psi.ft/min	-
Wear Rate	-	31.4m/min, 1.75MPa	mg/km	0.11	-	-
K-Factor	-	31.4m/min, 1.75MPa	mm³/Nm	2.2x 10 ⁵	in³.min./ft.lb.hr	1.0 x 10 ⁴
THERMAL						
Melting Temperature	-	-	°C	222	°F	432
Glass Transition Temperature (Tg)	ISO 11359-2:1999	-	°C	65	°F	149
Heat Deflection Temperature HDT/A	ISO 75	1.80MPa	°C	75	°F	176
Heat Deflection Temperature HDT/B	ISO 75	0.45MPa	°C	-	°F	-
Maximum Intermittent Service Temperature	-	-	°C	170	°F	338
Maximum Continuous Service Temperature	-	5000hrs	°C	110	°F	230
Minimum Intermittent Service Temperature	-	-	°C	-100	°F	-148
Minimum Continuous Service Temperature	-	-	°C	-40	°F	-40
Coefficient of Linear Thermal Expansion (TMA)	ISO 11359-2:1999	23°C - 55°C	°C ⁻¹	8 x 10 ⁻⁵	°F ⁻¹	0.44 x 10 ⁻⁵
Thermal Conductivity	ISO 8301:1991	Mean T = 20°C	W/m.°C	0.25	BTU in/ft.hr.°F	0.14
Flammability	IEC 60695-11-10:2003-08	-	-	HB	-	HB
ELECTRICAL						
Dielectric Constant	IEC 60250:1969-01	1MHz	-	3.7	-	3.7
Dielectric Constant (Low Frequency)	-	100Hz	-	4	-	4
Dissipation Factor	IEC 60250:1969-01	100Hz	Hz	0.014	Hz	0.014
Dielectric Strength	IEC 60243-1:1998-01	-	kV/mm	25	kV/in	635
Volume Resistivity	IEC 60093:1980-01	-	ohm.m	>1 x 10 ¹³	ohm.in	3.93 x 10 ¹⁴
Surface Resistivity ROA	IEC 60093:1980-01	-	ohm	>1 x 10 ¹²	ohm	1 x 10 ¹²
Comparative Tracking Index	IEC 60112:2003-01	-	CTI	600	CTI	600

AVAILABILITY



All information contained in this literature corresponds with our current knowledge of the products. Tynic Automation assume no liability whatsoever in respect of application, conversion or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, conversion or use of the aforementioned information or products. Existing intellectual property rights must be observed and Tynic Automation reserve the right to make technical alterations.