

This grade was specifically developed for applications requiring high impact resistance. Other important characteristics are improved insensitivity against stresses, sharp edges, notches and scratches. It also exhibits improved noise reduction and great load bearing capabilities.

PROPERTY	TEST METHOD	NOTES	METRIC UNITS		IMPERIAL UNITS	
Colour					Grey	
Density	ISO1183:1997	Test Method A	g/cm ³	1.110	lb/inch ³	0.040
Moisture Absorption (Equilibrium)	ISO 62:1999	50% RH, 23C	%	1.7	%	1.7
Water Absorption (24 Hours)	ISO 62:1999 (modified)	Immersion, 23C	%	0.18	%	0.18
Water Absorption (Saturation)	ISO 62:1999	Immersion, 23C	%	5.3	%	5.3
FDA Compatibility		NO				

MECHANICAL						
Tensile strength	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	60-70	psi	8702-10152
E-modulus	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	3100-3400	psi	449617-493128
Elongation at break	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	%	<10	%	<10
Compressive Strength	ISO 604:2002	Sample Type B, 5mm min ⁻¹	MPa	115-125	psi	16679-18129
Compressive Modulus	ISO 604:2002	Sample Type A, 1mm min ⁻¹	MPa	2300-2700	psi	333586-391601
Flexural Strength*	ISO 178:2001	1.5mm min ⁻¹	MPa	92-95	psi	13343-13778
Flexural Modulus	ISO 178:2001	1.5mm min ⁻¹	MPa	2300-2600	psi	333586-377098
Izod Impact Strength	ISO 180:2000	Sample Type A (Notched)	KJ/m ²	13.9	ft.lb/in ²	6.61
Charpy Impact Strength	ISO 179-2:1999	Notched	KJ/m ²	-	ft.lb/in ²	-
Hardness (Shore D)	ISO 868:2003	-	-	80	-	80
Coefficient of Friction (Dynamic)	-	31.4m/min, 1.75MPa	-	0.195	-	0.19
Limiting PV	-	-	MPa/m.min	100	psi.ft/min	-
Wear Rate	-	31.4m/min, 1.75MPa	mg/km	0.11	-	-
K-Factor	-	31.4m/min, 1.75MPa	mm ³ /Nm	3.5 x 10 ⁻⁵	in ³ .min./ft.lb.hr	1.7 x 10 ⁻⁴

THERMAL						
Melting Temperature	-	-	°C	219.5	°F	427
Glass Transition Temperature (Tg)	ISO 11359-2:1999	-	°C	60	°F	140
Heat Deflection Temperature HDT/A	ISO 75	1.80MPa	°C	72	°F	162
Heat Deflection Temperature HDT/B	ISO 75	0.45MPa	°C	-	°F	-
Maximum Intermittent Service Temperature	-	-	°C	150	°F	302
Maximum Continuous Service Temperature	-	5000hrs	°C	100	°F	212
Minimum Intermittent Service Temperature	-	-	°C	-100	°F	-148
Minimum Continuous Service Temperature	-	-	°C	-40	°F	-40
Coefficient of Linear Thermal Expansion (TMA)	ISO 11359-2:1999	23°C - 55°C	°C ⁻¹	8 x 10 ⁻⁵	°F ⁻¹	0.44 x 10 ⁻⁵
Thermal Conductivity	ISO 8301:1991	Mean T = 20°C	W/m.°C	0.26	BTU in/ft.hr.°F	0.15
Flammability	IEC 60695-11-10:2003-08	-	-	HB	-	HB

ELECTRICAL						
Dielectric Constant	IEC 60250:1969-01	1MHz	-	3.7	-	3.7
Dielectric Constant (Low Frequency)	-	100Hz	-	4	-	4
Dissipation Factor	IEC 60250:1969-01	100Hz	Hz	0.09	Hz	0.09
Dielectric Strength	IEC 60243-1:1998-01	-	kV/mm	25	kV/in	635
Volume Resistivity	IEC 60093:1980-01	-	ohm.m	>1 x 10 ¹³	ohm.in	3.93 x 10 ¹⁴
Surface Resistivity ROA	IEC 60093:1980-01	-	ohm	>1 x 10 ¹²	ohm	1 x 10 ¹²
Comparative Tracking Index	IEC 60112:2003-01	-	CTI	600	CTI	600

AVAILABILITY



All information contained in this literature corresponds with our current knowledge of the products. Tynic Automation assume no liability whatsoever in respect of application, conversion or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, conversion or use of the aforementioned information or products. Existing intellectual property rights must be observed and Tynic Automation reserve the right to make technical alterations.