

**Raw Material** High-Density Polyethylene (HDPE)



General Properties	Test Method	Unit	Value
Density	DIN EN ISO 1183	g/cm <sup>3</sup>	0.955
Water Absorption in air 50% r.h.	DIN 53715	%	0
Absorption 23-C In Water-Saturation	DIN 53495	%	0.02
Food Compliance	-	FDA/BfR	YES
UV Stability	-	-	YES
Mechanical Properties			
Tensile Stress At Yield At Break	DIN 53455	N/mm <sup>2</sup>	30
Elongation At Break	DIN 53453	%	500
Tensile Modulus Of Elasticity	DIN 53456	N/mm <sup>2</sup>	800
Compression Test 1% Strain 1000h	DIN 53444	N/mm <sup>2</sup>	3
Notched Impact Strength (Charpy)	DIN 53455	KJ/mm <sup>2</sup>	12
Ball Indentation Hardness	DIN 53453	N/mm <sup>2</sup>	40
Shore Hardness (D)	DIN 53456	Scale D	63
Coefficient Of Friction To Steel	DIN 53375	u	0.32
Thermal Properties			
Melting Temperature	ISO 3146	°C	130
Thermal Conductivity	DIN 52612	W/km	0.39
Deformation at temperature HDT	DIN 53461	°C	45
Coefficient Of Linear Thermal Expansion	DIN 53752	10 <sup>-6</sup> K <sup>-1</sup>	180
Service Temperature, Long Term	Average	°C	80
Service Temperature, Short Term (MAX)	Average	°C	90
Minimum Operating Temperature	Average	°C	-50
Flammability	UL 94 (3-6mm thickness)	-	HB
Electrical Properties			
Dielectric Constant at 1 MHz	DIN 53483	-	2.3
Dielectric Dissipation Factor (1 MHz)	DIN 53483	-	0.0006
Volume Resistivity	DIN 53482	Ωcm	10 <sup>15</sup>
Dielectric Strength	DIN 53481	KV/mm	45

**Applications:**

- Chemical Vessels
- Storage Tanks
- Conveyor Components & Rollers
- Cutting Boards
- Bulk Solid Bins & Hoppers

**Characteristics:**

- Extremely Light Weight & Tough
- Excellent Wear Resistance
- Good Chemical Resistance
- Low Co-efficient Of Friction



All information contained in this literature corresponds with our current knowledge of the products. Tynic Automation assume no liability whatsoever in respect of application, conversion or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, conversion or use of the aforementioned information or products. Existing intellectual property rights must be observed and Tynic Automation reserve the right to make technical alterations.